


# Çok Telli Çelik Halatlar / Steel Wire Ropes

## EN 12385

Warrington  
Seale



6x36 WS  
6[1+7+(7+7)+14]  
ÇÖ/IWRC

Halat Çapı Rope Diameter	Birim Ağırlık Unit Weight	Minimum Kopma Kuvveti (kN) Minimum Breaking Load (MBL)	
		1770 N/mm <sup>2</sup> IPS	1960 N/mm <sup>2</sup> EIPS
mm	kg/m		
8,00	0,262	40,3	44,7
9,00	0,331	51,0	56,5
10,00	0,409	63,0	69,8
11,00	0,495	76,2	84,4
12,00	0,589	90,7	100,5
13,00	0,691	106,5	117,9
14,00	0,802	124	137
15,00	0,920	142	157
16,00	1,047	161	179
17,00	1,182	182	202
18,00	1,325	204	226
19,00	1,476	227	252
20,00	1,636	252	279
21,00	1,804	278	308
22,00	1,980	305	338
23,00	2,164	333	369
24,00	2,356	363	402
25,00	2,566	394	436
26,00	2,765	426	472
27,00	2,982	459	509
28,00	3,207	494	547
29,00	3,440	530	587
30,00	3,681	567	628
31,00	3,930	606	671
32,00	4,188	645	715
33,00	4,454	686	760
34,00	4,728	728	807
35,00	5,010	772	855
36,00	5,301	817	904
37,00	5,599	863	955
38,00	5,906	910	1008
39,00	6,221	958	1061
40,00	6,544	1008	1116
41,00	6,875	1059	1173
42,00	7,215	1112	1231
43,00	7,562	1165	1290
44,00	7,918	1220	1351
46,00	8,654	1333	1476
48,00	9,423	1452	1608
50,00	10,225	1575	1744
52,00	11,059	1704	1887
56,00	12,826	1976	2188
60,00	15,155	2268	2512
64,00	17,375	2581	2858

ISO 4309'a göre; RCN: 09 / According to ISO 4309; RCN: 09



Kullanım Alanları / Applications Areas



Madencilik  
Mining



Petrol Kuyuları  
Oil Industry



Denizcilik  
Marina



Genel Yük Kaldırma  
General Lifting



Mühendislik  
Engineering



Fore Kazık  
Drilling