


## Çok Telli Çelik Halatlar / Steel Wire Ropes

### EN 12385

Warrington  
Seale



6x36 WS  
6[1+7+(7+7)+14]  
LÖ/FC

Halat Çapı Rope Diameter	Birim Ağırlık Unit Weight	Minimum Kopma Kuvveti (kN) Minimum Breaking Load (MBL)	
		1770 N/mm <sup>2</sup> IPS	1960 N/mm <sup>2</sup> EIPS
8,00	0,235	37,4	41,4
9,00	0,297	47,3	52,4
10,00	0,367	58,4	64,7
11,00	0,444	70,7	78,3
12,00	0,528	84,1	93,1
13,00	0,620	98,7	109,3
14,00	0,719	114	127
15,00	0,826	131	146
16,00	0,940	150	166
17,00	1,061	169	187
18,00	1,189	189	210
19,00	1,325	211	233
20,00	1,468	234	259
21,00	1,618	258	285
22,00	1,776	283	313
23,00	1,941	309	342
24,00	2,114	336	373
25,00	2,294	365	404
26,00	2,481	395	437
27,00	2,675	426	472
28,00	2,877	458	507
29,00	3,086	491	544
30,00	3,303	526	582
31,00	3,527	561	622
32,00	3,758	598	662
33,00	3,997	636	704
34,00	4,243	675	748
35,00	4,496	716	792
36,00	4,756	757	838
37,00	5,024	800	885
38,00	5,299	843	934
39,00	5,582	888	984
40,00	5,872	935	1035
41,00	6,169	982	1087
42,00	6,474	1030	1141
43,00	6,786	1080	1196
44,00	7,105	1131	1252
46,00	7,766	1236	1369
48,00	8,456	1346	1490
50,00	9,175	1460	1617
52,00	9,924	1579	1749
54,00	10,702	1703	1886
56,00	11,509	1832	2028
58,00	12,346	1965	2175

ISO 4309'a göre; RCN: 09 / According to ISO 4309; RCN: 09

### Kullanım Alanları / Applications Areas



Madencilik  
Mining



Petrol Kuyuları  
Oil Industry



Denizcilik  
Marina



Genel Yük Kaldırma  
General Lifting



Mühendislik  
Engineering