


Çok Telli Çelik Halatlar / Steel Wire Ropes

EN 12385

Warrington
Seale



8x36 WS
8[1+7+(7+7)+14]
ÇÖ/IWRC

Halat Çapı Rope Diameter	Birim Ağırlık Unit Weight	Minimum Kopma Kuvveti (kN) Minimum Breaking Load (MBL)	
		1770 N/mm ² IPS	1960 N/mm ² EIPS
mm	kg/m		
10,00	0,435	63,0	69,8
11,00	0,526	76,2	84,4
12,00	0,626	90,7	100,5
13,00	0,735	106,5	117,9
14,00	0,853	124	137
15,00	0,979	142	157
16,00	1,114	161	179
17,00	1,257	182	202
18,00	1,409	204	226
19,00	1,570	227	252
20,00	1,740	252	279
21,00	1,918	278	308
22,00	2,105	305	338
23,00	2,301	333	369
24,00	2,506	363	402
25,00	2,719	394	436
26,00	2,941	426	472
27,00	3,171	459	509
28,00	3,410	494	547
29,00	3,658	530	587
30,00	3,915	567	628
31,00	4,180	606	671
32,00	4,454	645	715
33,00	4,737	686	760
34,00	5,029	728	807
35,00	5,329	772	855
36,00	5,638	817	904
37,00	5,955	863	955
38,00	6,281	910	1008
39,00	6,616	958	1061
40,00	6,960	1008	1116
41,00	7,312	1059	1173
42,00	7,673	1112	1231
43,00	8,043	1165	1290
44,00	8,422	1220	1351
46,00	9,205	1333	1476
48,00	10,022	1452	1608
50,00	10,875	1575	1744
52,00	11,762	1704	1887
54,00	12,685	1837	2035
56,00	13,642	1976	2188
58,00	14,633	2120	2347
60,00	15,660	2268	2511

ISO 4309'a göre; RCN: 13 / According to ISO 4309; RCN: 13



Kullanım Alanları / Applications Areas



Mühendislik
Engineering



Genel Yük Kaldırma
General Lifting